

In the Claims:

1. (Original) A catalyst for removing nitrogen oxides which is used to denitrify exhaust gas containing nitrogen oxides, which comprises: at least one kind of oxide selected from the group consisting of copper oxides, chromium oxides, and iron oxides; and which further comprises: at least one kind of titanium oxide; at least one kind of tungsten oxide; and at least one kind of vanadium oxide.
2. (Original) A catalyst for removing nitrogen oxides which is used to denitrify exhaust gas containing at least NO_2 , which comprises: at least one kind of oxide selected from the group consisting of copper oxides, chromium oxides, and iron oxides as a component for reducing NO_2 to NO ; and which further comprises: at least one kind of titanium oxide; at least one kind of tungsten oxide; and at least one kind of vanadium oxide as components for reducing NO to N_2 .
3. (Original) The catalyst for removing nitrogen oxides according to claim 2, wherein the component for reducing NO_2 to NO consists of a copper oxide.
4. (Currently Amended) The catalyst for removing nitrogen oxides according to claim 3, wherein the oxides are contained so that 5 to 23 tungsten, 0.1 to 5 vanadium, and 5 or less copper are contained with respect to 100 titanium in atomic ratio.
5. (Original) The catalyst for removing nitrogen oxides according to claim 2, wherein the component for reducing NO_2 to NO consists of a chromium oxide.
6. (Currently Amended) The catalyst for removing nitrogen oxides according to claim 5, wherein the oxides are contained so that 5 to 23 tungsten, 0.1 to 5 vanadium, and 5 or less chromium are contained with respect to 100 titanium in atomic ratio.
7. (Original) The catalyst for removing nitrogen oxides according to claim 2,

wherein the component for reducing NO_2 to NO consists of an iron oxide.

8. (Currently Amended) The catalyst for removing nitrogen oxides according to claim 7, wherein the oxides are contained so that 5 to 23 tungsten, 0.1 to 5 vanadium, and 5 or less iron are contained with respect to 100 titanium in atomic ratio.

9. (Original) A catalyst molded product for the catalyst for removing nitrogen oxides as described in claim 2, wherein the catalyst molded product is obtained by mixing the component for reducing NO to N_2 with the component for reducing NO_2 to NO .

10. (Original) A catalyst molded product for the catalyst for removing nitrogen oxides as described in claim 2, wherein the catalyst molded product is formed by carrying the component for reducing NO_2 to NO on the component for reducing NO to N_2 and then by molding.

11. (Original) A catalyst molded product for the catalyst for removing nitrogen oxides as described in claim 2, wherein the catalyst molded product is formed by carrying the component for reducing NO_2 to NO on a molded product molded by using the component for reducing NO to N_2 .

12. (Currently Amended) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 1-~~or~~2.

13. (Currently Amended) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 1-~~or~~2, wherein the NO_2/NO ratio in exhaust gas to be treated is 1 or higher.

14. (Currently Amended) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 1-~~or~~2, wherein the O_2 concentration in exhaust

gas to be treated is 6 percent or higher by volume.

15. (Original) The catalyst for removing nitrogen oxides according to claim 1, wherein said catalyst further comprises a molybdenum oxide.

16. (Original) The catalyst for removing nitrogen oxides according to claim 2, wherein said catalyst comprises a molybdenum oxide as a component for reducing NO to N₂.

17. (Original) A catalyst for removing nitrogen oxides which removes nitrogen oxides in exhaust gas by reduction in the presence of ammonia, wherein a first catalyst which is highly active in removing nitrogen dioxide is arranged on the upstream side in the exhaust gas flow direction, and a second catalyst which is highly active in removing nitrogen monoxide is arranged on the downstream side of said first catalyst in the exhaust gas flow direction.

18. (Original) A catalyst for removing nitrogen oxides which removes nitrogen oxides in exhaust gas by reduction in the presence of ammonia, wherein a first catalyst which is highly active in removing nitrogen dioxide is arranged on the upstream side in the exhaust gas flow direction, and a second catalyst which is highly active in removing nitrogen monoxide is arranged on the downstream side of said first catalyst in the exhaust gas flow direction, and
as said second catalyst, a catalyst comprising a titanium oxide as a first component and at least one or more kinds of vanadium oxide, tungsten oxide, and molybdenum oxide as a second component is applied, and

as said first catalyst, a catalyst in which said second catalyst comprises at least one or more kinds of copper oxide and chromium oxide as a third component is applied.

19. (Original) A catalyst for removing nitrogen oxides which removes nitrogen oxides in exhaust gas by reduction in the presence of ammonia, wherein
a second catalyst consisting of a catalyst comprising a titanium oxide as a first component and a vanadium oxide and a tungsten oxide as second components, and

a first catalyst consisting of a catalyst in which said second catalyst comprises a composite oxide of copper oxide and chromium oxide as a third component are arranged in combination.

20. (Original) A catalyst for removing nitrogen oxides which removes nitrogen oxides in exhaust gas by reduction in the presence of ammonia, wherein

a second catalyst consisting of a catalyst comprising a titanium oxide as a first component and a vanadium oxide and a tungsten oxide as second components, and

a first catalyst consisting of a catalyst in which said second catalyst comprises a composite oxide of copper oxide and chromium oxide as a third component are combined, and

said first catalyst is arranged on the upstream side in the exhaust gas flow direction, and said second catalyst is arranged on the downstream side of said first catalyst in the exhaust gas flow direction.

21. (Original) The catalyst for removing nitrogen oxides according to claim 20, wherein

said catalyst comprises a molybdenum oxide as the second component of said second catalyst.

22. (Original) A catalyst for removing nitrogen oxides which removes nitrogen oxides in exhaust gas by reduction in the presence of ammonia, wherein

a second catalyst consisting of a catalyst comprising a titanium oxide as a first component and at least one or more kinds of vanadium oxide, tungsten oxide, and molybdenum oxide as a second component, and

a first catalyst consisting of a catalyst in which said second catalyst comprises at least one or more kinds of copper oxide and chromium oxide as a third component are arranged in combination.

23. (Currently Amended) The catalyst for removing nitrogen oxides according to ~~any one of claims 17, 18, 20 and 21~~, wherein

at least not less than 1/4 and less than 4/4 of an upstream catalyst flow path length in the exhaust gas flow direction is constituted by said second catalyst, and

a downstream catalyst flow path length in the exhaust gas flow direction is constituted by said first catalyst.

24. (Currently Amended) An exhaust gas treating method using the catalyst for removing nitrogen oxides according to ~~any one of claims 15 to 23~~.

25. (Currently Amended) A combined cycle power generation facility comprising:
a compressor for compressing air;

burning means for burning compressed air compressed by said compressor and a fuel;

a gas turbine for generating electric power by expanding combustion gas sent from said burning means to obtain an output;

an exhaust heat recovery boiler in which exhaust from said gas turbine is sent and steam is generated, and the catalyst for removing nitrogen oxides according to ~~any one of claims 17 to 23~~ is arranged;

a steam turbine for generating electric power by expanding steam generated by said exhaust heat recovery boiler to obtain an output;

condensing means for condensing exhaust steam of said steam turbine; and

supply means for supplying condensed water condensed by said condensing means to said exhaust heat recovery boiler.

26. (New) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 2.

27. (New) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 2, wherein the NO₂/NO ratio in exhaust gas to be treated is 1 or

higher.

28. (New) An exhaust gas treating method using the catalyst for removing nitrogen oxides as described in claim 2, wherein the O₂ concentration in exhaust gas to be treated is 6 percent or higher by volume.

29. (New) The catalyst for removing nitrogen oxides according to claim 18, wherein at least not less than 1/4 and less than 4/4 of an upstream catalyst flow path length in the exhaust gas flow direction is constituted by said second catalyst, and a downstream catalyst flow path length in the exhaust gas flow direction is constituted by said first catalyst.

30. (New) The catalyst for removing nitrogen oxides according to claim 20, wherein at least not less than 1/4 and less than 4/4 of an upstream catalyst flow path length in the exhaust gas flow direction is constituted by said second catalyst, and a downstream catalyst flow path length in the exhaust gas flow direction is constituted by said first catalyst.

31. (New) The catalyst for removing nitrogen oxides according to claim 21, wherein at least not less than 1/4 and less than 4/4 of an upstream catalyst flow path length in the exhaust gas flow direction is constituted by said second catalyst, and a downstream catalyst flow path length in the exhaust gas flow direction is constituted by said first catalyst.